

**P9R6K-054X**

**DESCRIPTION:** Random Copolymer

**FEATURES:** Excellent clarity. High flow material. Product does not contain any animal derived components. Phthalate-free.

**APPLICATIONS:** Injection molding: High clarity applications. A replacement for PET, PS and PC high clarity applications.

PROPERTY	NOMINAL VALUE	SI UNIT	NOMINAL VALUE	ENGLISH UNIT	ASTM TEST METHOD
Melt Flow Rate	35	g/10 min.			D 1238
Density	0.9	g/cm <sup>3</sup>			D 1505
Tensile Yield Strength	28	MPa	4060	psi	D 638
Yield Elongation	14	%	14	%	
Flexural Modulus 1% Secant Tangent	919 972	MPa	133 141	kpsi	D 790
Deflection Temperature @ 66 psi (.455 MPa)	78	°C	172	°F	D 648
Rockwell Hardness			97	R	D 785
Notched Izod @ 23°C	79	J/m	1.5	ft-lb/in	D 256
Haze @ 25 mil @ 50 mil	2.8 5.8	%	2.8 5.8	%	D 1003

March-09 Developmental product values are based on limited data. Product may not be commercially available.

Contact your sales representative for information



**REGULATORY**

FDA - 21 CFR 177.1520 (c) 3.1a

118 Huntsman Way, Longview, TX 75602 · Tel: 1-800-985-7303

The data and information represented herein refer to typical values obtained in our laboratories by the methods or apparatuses indicated, and should be so considered. Since processing variables are a major factor in product performance, this information should serve only as a guide. Since customers' testing conditions are outside our control, the reproducibility of our data in a customer's testing facility is not guaranteed. Customer should confirm results under its testing conditions. There is no implied warranty of merchantability or fitness for a particular purpose. Establishing satisfactory performance of the product for the intended application is the customer's sole responsibility. No warranty is given concerning the existence or non-existence of any patents claiming any pertinent subject matter presented herein. The Company assumes no obligation, express or implied, or liability for use of or reliance on the information and data presented. FHR disclaims all product warranties expressed or implied, including warranties of fitness for particular purpose or of merchantability. Further, this product is not intended for use in the manufacture of any form of implanted medical or surgical device.